



TWO PACK EPOXY RED OXIDE PRIMER



DESCRIPTION:

Gamma 2 Pack Epoxy Red Oxide Primer is a high build, modified, 2 Component Epoxy paint with good wetting properties and low water permeability. It is self priming and forms a hard and tough coating which has good resistance against abrasion and impact as well as to seawater, mineral oils, aliphatic hydrocarbons and splashes from petrol and related Products.

USES:

It is designed for use in steel & concrete surfaces in severe industrial or marine environments. It can work as a finishing coat where cosmetic appearance is of less importance.

MAIN FEATURES:

- Excellent durability to all types of chemical environment.
- Outstanding adhesion to wide variety of surfaces.

SURFACE PREPARATION:

Prepare surface by method suitable for exposure and service. Always clean off any contamination between coats prior to applying subsequent topcoats.

- I. **New steel:** Oil and grease must be removed with suitable detergent, salts and other contaminants by (high pressure) fresh water cleaning prior to blasting. After blasting, clean the surface carefully from abrasives and dust. Abrasive blasting is the most effective method. Ensure surfaces are completely dry in depth and free of dirt, oil, grease or other contamination.
- II. **Maintenance:** On old steel surfaces having been exposed to salt water, excessive amounts of salt residues in pitting may call for wet abrasive blasting followed by dry abrasive blasting. Alternatively, dry abrasive blasting followed by high pressure fresh water cleaning, drying, and finally, dry abrasive blasting again.

Note: Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

For Further Information, please contact us at:

Yemen Company for Paints & Derivatives Ltd.

Tel. +967-4-205570/72

E-mail: info@ycpd.biz





| Physical Properties | |
|----------------------|--|
| Color | Red Oxide |
| Finish | Flat |
| Curing Mechanism | Cross linking reacting between epoxy and polyamide |
| Mixing Ratio | Base to Hardener (3 : 1 by weight) |
| Type of Solvent | Toluene /Xylene, Methoxy Propanol |
| Volume Solid | 48 ± 1 % |
| Weight Solid | 75 ± 1 % |
| Specific Gravity | 1.5 ± 0.02 |
| Flash Point | 30°C |
| VOC | 450 gm / lt. |
| Dry Film Thickness | 60 – 75 µ for one coat |
| Theoretical Coverage | 6.0 – 6.5 m ² / lt. for one coat |
| Practical Coverage | Depends on nature of surface |
| Shelf Life | 12 months |

| Application Details | |
|-----------------------|---|
| Substrate | Mechanically cleaned Steel or Concrete surface |
| Thinner | Normally not necessary. If desired, with Epoxy Thinner max. (5-10%) |
| Mixing | Mix base component uniformly before adding hardener, then combine at recommended ratio & mix thoroughly for at least 2-3 minutes. Keep the added mixtures for 5 – 10 minutes for complete reaction, before the start of application |
| Pot life@ 30°C | 3 – 4 Hours |
| Application Condition | 25°C – 40°C / 50 – 70 RH |
| Clean Up | With Epoxy Thinner |
| Application Method | Airless or conventional spray. Touch- up can be made with brush or roller |
| Drying Time @ 30°C | Tack-Free (3 – 4 Hours) in 60 – 70% RH. Recoat * (> 18 hrs & < 24 hrs) |

*If Recoat time is exceeded, slight sanding with sand paper is necessary, to create a surface profile.

| Performance Characteristics | |
|-------------------------------------|--|
| Impact Resistance | > 120 cm.kg - By ASTM – D 2794 |
| Flexibility | 1 / 4" – By ASTM – D 173 (By Conical Mandrel) |
| Hardness | ISO Class – II – By ISO 2409 (By Cross Cut Hardness Tester) |
| Salt Fog Exposure | No Blistering / rusting for 1000 hours. – By ASTM – B 117 |
| Safety Health & Environment (S.H.E) | Handle with care – Strictly follow the handling, storage and use instruction on paint cans and /or MSDS including the personal protection equipment necessary during application. Always preferred to apply in well ventilated areas. |

For Further Information, please contact us at:

Yemen Company for Paints & Derivatives Ltd.

Tel. +967-4-205570/72

E-mail: info@ycpd.biz

