



ATLAS ALUMINIUM

DESCRIPTION:

Atlas Aluminum is a high quality alkyd based paints containing special aluminum peels which provides the best light reflection and heat resistivity up to 235°C.

USES:

As a general purpose primer for protection of steel substrates in mild atmospheric corrosive environment.

| Technical Data | |
|----------------------------|--|
| Product Type | Solvent Based |
| Color | Silver and Golden |
| Finish variants | Flat |
| Weight Solid | 62-65 % |
| Specific Gravity | 1.32-1.32 g/ml |
| Viscosity @ 25°C | 400-450 gm |
| Touch Dry | 3-4 Hours @ 25°C |
| Flash Point | <30 °C |
| Thinner | Atlas Thinner : Turpentine |
| Stability of Thinned paint | |
| Theoretical Coverage | 13 m ² / lt. for one coat. (Dependable on surface conditions & application methods) |
| Packs Offered | 17L, 3.5L, 1L, 400ml |
| Shelf Life | 2 years from the date of manufacture in original tightly closed containers away from direct sunlight and excessive heat. |

Application Details

| | |
|---------------------|---|
| Application Method | Airless spray, Air spray, Brush or Roller |
| Thinning Volume | 20 % |
| Re-Coating Interval | Minimum 24 Hours |
| Preceding Coat | - |

For Further Information, please contact us at:

Yemen Company for Paints & Derivatives Ltd.

Tel. +967-4-205570/72

E-mail: info@ycpd.biz





Surface Preparation

| | |
|--------------------|---|
| New Steel | Surface should be clean, free of oil, grease, rust and dust residues. |
| Maintenance | Loose old paint must be removed thoroughly. Remove oil and grease. Remove salt and contamination. |

* Recoating Interval was quoted for 28 – 30°C and at 60 – 65% Relative Humidity

Precautions

1. Kindly refer to MSDS for detailed safety measures while handling the paint.
2. Store the product in ambient conditions in well ventilated locations and away from source of ignition and fire.
3. Avoid eye and skin contact. In case it happens, wash with plenty of clean water.
4. Do not inhale or inject. In case of inhalation move to fresh air.
5. Use protective equipments like globes, safety glasses, face mask while handling the paint – this is required for all paint.
6. Do not apply when the ambient temperature is less than 10°C or it might drop to this level within 4 hours of application.
7. Both white and tinted paints need through shaking / mixing immediately before use.
8. Where ever dilution is necessary, use pure water. Adjust a viscosity of 30 – 40 sec for brush application and for other method use at 20 – 30 sec by Ford cup No. 4

Note: Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

For Further Information, please contact us at:

Yemen Company for Paints & Derivatives Ltd.

Tel. +967-4-205570/72

E-mail: info@ycpd.biz

